

GENERAL SUMMARY OF ANTHRACITE CHARACTERISTICS

(ALL ON A DRY BASIS)

	FROM	TO	AVERAGE	+/- STD DEV
ABSORPTION	5.18	21.00	7.849	3.146
ACID SOLUBILITY	0.00	2.60	0.431	0.570
ASH	6.40	33.83	12.31	3.62
BTU / POUND	12,007	12,861	12,496	260
CARBON, FIXED	60	87	82	4
CAUSTIC SOLUBILITY	0.000	3.400	0.519	0.556
HARDGROVE GINDABILTIY	28.0	49.0	38.4	4.1
FRIABILITY	0.00	8.10	1.301	1.596
MOH'S HARDNESS	2.0	4.0	3.13	0.25
MOISTURE, INHERENT	0.13	20.85	6.334	5.626
SPECIFIC GRAVITY, APPARENT	1.50	2.60	1.645	0.074
SULPHER	0.49	0.71	0.559	0.068
VOLATILES	3.89	8.85	5.709	0.849
%FLOAT @ 1.45	0.00	11.50	2.58	3.36
%SINK @ 1.95	0.00	14.60	2.21	2.77
DATE OF LAST ENTRY	10/24/2013			